

Zerust® Axxatec™ 80C

Zerust® Axxatec™ 80C는 수용성 방청유로 옥내 보관 시 철 금속을 1~2개월 정도 보호할 수 있다.

스프레이, Brushing, dipping 방법으로 적용할 수 있으며, 건조 후 접촉 가능한 보호 피막을 남긴다.

Zerust® Axxatec™ 80C는 Zerust만의 검증된 부식방지기술이 접목된 수용성 방청유이다.

Axxatec™ 80C는 건조가 빠르며 건조 후 표면에 잔류물이 거의 남지 않는 장점이 있다.

Axxatec™ 80C는 가공 공정 중 혹은 대형 장비의 일시 보관 중 부식 방지가 필요할 때 사용된다.

Zerust® 방청필름과 같이 사용하면 1년 이상의 기간 동안 부식방지가 가능하다.

도장, 고무, 플라스틱 물질에 영향을 주지 않고 폭 넓게 사용할 수 있다.

▶ 장 점

투명하고, 건조 후 접촉이 가능한 소수성 막 형성

탁월한 방청성능

적용과 제거가 용이

도장, 고무, 플라스틱 물질에 안전함.

적용 사례

Axxatec™ 80C는 Spray 또는 dipping 적용이 권장됨.

첨가 비율은 요구되는 보호 기간 따라 조절 가능



제품 적용

보관

운송

공정 대기 중

Zerust 방청 제품과 함께 사용



기술 정보

투명하고, 끈적이지 않는 보호를 위한 Axxatec 80C의 사용

제품 정보	수용성 방청유	
적용	Dipping, Brushing, 스프레이로 적용 적용 온도 10 ~ 32°C Dipping 시간 45초 흐르는 시간 0 ~ 15분 건조 시간 45 ~ 60분 희석 2 ~ 7.5% 점도@ (21°C) 650 cps @100rpm 사용량 73 m ² / Liter (7.5%로 사용) 두께 (적용 방법에 따라 다름) 6 ~ 12 μm	
특징	외관 도막 표면 상태 제거 휘발성 유기화합물 함량 어는점 pH	반투명 갈색 액체 투명, 건조 후 접촉 가능 알칼리 세척제 <35% 0° 약 6 ~ 9
방청 성능 및 적용 금속	옥내 옥외 포장/밀봉 포장 금속 종류	1~2개월 추천하지 않음 5년 정도 철 금속 전용 동 및 아연 사용불가
보관	온도 기간	10 ~ 32°C 2년 이하
폐기	지역, 국가, 국제 규정에 따라 폐기	

주의 사항

- 도포 후 도장 시 세척 필요.
- 아연 사용 중 잔량은 밀폐 보관.
- 도금 및 동 금속에 사용 금지.
- Axxatec™ 80C이 도포된 금속과 골판지나 목재의 직접 접촉 피할 것.

폐기

지역, 국가별 법률에 따라 표기

제품 규격 및 형태

- 20 liter / Pail
- 200 liter / Drum

Warranty and Disclaimer Information: We guarantee our products conform to documented quality specifications. Product information subject to change without notice. We make no warranty of any kind expressed or implied as to the effects of use (including, but not limited to, damage or injury). For full warranty and disclaimer information visit, www.zerust.com/warranty.

©2015 Northern Technologies International Corporation (NTIC). All Rights Reserved. NTIC is the owner of the following trademarks: ActivPak®, Cor-Tab®, EXCOR®, Flange Saver®, ICT®, NTI®, Plastabs®, Z-CIS®, Zerion®, ZERUST®, The ZERUST People®, and the Color "Yellow". ABRIGO®, UNICO®, and VALENO® are registered trademarks of EXCOR GmbH, a Joint Venture Partner of NTIC.

Contact Us



(주)한국지러스트
서울본사

부산영업소
기술연구소 & 대전공장

www.zerust.co.kr

서울특별시 금천구 시흥대로97, #A-203

TEL: 02-895-8891 FAX: 02-895-8895

TEL: 051-319-1730 FAX: 051-319-1731

대전광역시시 대덕구 방두말4길 29

TEL: 042-936-8891 FAX: 042-936-8895