

Zerust® Axxanol™ 33CD

Zerust® Axxanol™ 33CD는 속건성 방청유로서 건조 후 빠른 시간 내에 건조된다.

도포 후 얇은 막을 형성하여 옥내 보관 시 1~2개월 보관이 가능하며, Zerust® 방청 필름과 함께 사용하면 더 오랜 기간 동안 철 금속을 부식으로부터 보호할 수 있다.

Zerust® Axxanol™ 33CD는 독자의 지러스트® 부식방지첨가제가 함유된 사용하기 편리한 방청유이다.

Zerust® Axxanol™ 33CD는 스프레이 또는 Brushing 후, 빨리 건조되어 얇은 방청피막을 형성하도록 설계되어졌다.

Zerust® Axxanol™ 33CD를 Zerust® 철용필름과 같은 Zerust® 제품과 함께 사용한 경우, 방청기간은 최대 5년까지 연장가능하다. (옥내보관조건)

Zerust® Axxanol™ 33CD는 부품에 도포된 후 짧은 시간 (약 1시간) 내에 마르기 때문에 오일 성분에 의한 사고나 오염을 피할 수 있다.

사용자는 피막이 있는 부품을 다룰 때 사용해야하는 마스크나 보안경과 같은 개인 보호 장비를 착용할 필요가 없는 장점이 있다.

적용 사례

- 매니폴드에 Axxanol 33CD 도포
- Zerust 방청필름 포장
- 빠른 건조
- 작업장 청결 유지



▶ 장 점

Zerust® 방청 필름과 같이 사용 가능

도포 후 빠른 건조

적은 냄새

도장 전 세척 용이

제품 적용

보관

운송 과정 중

Zerust® 방청 필름과 같이 사용 가능



기술 자료

Zerust® Axxanol™ 33CD 단독 사용 혹은 Zerust 방청 포장과 함께 사용

제품 정보	용제희석형 속건성 방청유. 노란색의 투명한 액체로 건조 후 피막이 눈에 보이지 않으며, 끈적거림이 매우 적음	
적용	스프레이 혹은 Brushing 방법으로 적용	
	적용 온도	10 ~ 30°C
	범위 (dipping 적용)	35 m ² / Liter
	막 두께	약 12 µm
특징	제거 방법	알칼리세척제
	휘발성 유기화합물 함량	98-100%
	인화점	38°C
	점도	60 cPsat 73°C
제품 정보	옥내방청기간	1~2개월 정도
	옥외방청기간	추천하지 않음
	포장/밀봉	5년 정도
	금속 종류	철, 주철 및 아연 (동 금속 사용금지)
보관	온도	0 ~ 30°C
	기간	2년 이하

제품 규격 및 형태

- 20 liter / Pail
- 200 liter / Drum
- 360 ml / Aerosol Can

폐기

지역, 국가별 법률에 따라 폐기

작업 정보

피막을 건조시킬 때, 개인 보호 용품은 필요 없음. 금속의 부식과 오염을 방지하기 위해서 보푸라기가 없는 깨끗한 장갑을 사용.

Warranty and Disclaimer Information: We guarantee our products conform to documented quality specifications. Product information subject to change without notice. We make no warranty of any kind expressed or implied as to the effects of use (including, but not limited to, damage or injury). For full warranty and disclaimer information visit, www.zerust.com/warranty.

©2015 Northern Technologies International Corporation (NTIC). All Rights Reserved. NTIC is the owner of the following trademarks: ActivPak®, Cor-Tab®, EXCOR®, Flange Saver®, ICT®, NTI®, Plastabs®, Z-CIS®, Zerion®, ZERUST®, The ZERUST People®, and the Color "Yellow". ABRIGO®, UNICO®, and VALENO® are registered trademarks of EXCOR GmbH, a Joint Venture Partner of NTIC.

Contact Us

ZERUST® EXCOR

(주)한국지러스트
서울본사

부산영업소
기술연구소 & 대전공장

www.zerust.co.kr
서울특별시 금천구 시흥대로97, #A-203

TEL: 02-895-8891 FAX: 02-895-8895

TEL: 051-319-1730 FAX: 051-319-1731

대전광역시시 대덕구 방두말4길 29

TEL: 042-936-8891 FAX: 042-936-8895